

A-300

Solvent Cast Acrylic Film

Is a solvent cast acrylic film. It can be formulated with a stabilizer package to provide for the best weatherability.

Benefits

- Superior clarity
- Low haze
- Good weatherability
- Good adhesion

Not FDA Compliant: Not compliant for use in food contact applications.



Revision Date:	11/19/12		
Property	Units	Typical Value	Test Method
Specific Gravity		1.14	
Yield	Sq. in./lbs/mil	24,280	Calculated
Tensile Strength	PSI, 1.0 mil	3394	
Ultimate Elongation	%, 1.0 mil	112	
Heat Sealing	Degrees F	< 325	
Shrinkage MD, TD	@ 200°F / 10 mins, 1.0 mil	7 %, 7 %	
Haze	%	0.9 to 1.7 %	BYK Gardner Haze-Gard Plus meter
Transmittance	%	94 to 95 %	BYK Gardner Haze-Gard Plus meter
Gloss	60°	132	BYK Gardner micro TRI-gloss meter



The information and suggestions contained herein represent the best information available to VCF Films, Inc., and we believe them to be reliable. They should not, however, be construed as controlling and are present without guarantee of performance either express or implied. We urge purchasers to conduct confirmatory tests to determine final suitability for their specific use. No statement with respect to use is intended as a positive recommendation for such use and no warranty with respect to infringement of patents held by others is made or intended.

VCF Films, Inc. • 1100 Sutton, Howell, MI 48843 • 888-905-7680 • Fax 517-546-2984 • www.vcffilms.com