



VCF FILMS, Inc.

SPECIALTY FILMS --- PRODUCT INFORMATION

Clear Polyurethane

Property	Units	Typical Value	Test Method/Apparatus
Thickness:	mils	6.4	
Specific Gravity:		1.11	Calculated
Yield:	inch ² *mil/lb	24,900	Calculated
Haze		0.93%	
Transmittance	90 deg.	93.7%	
Shrink (MD/TD)	120°F, 30 min	0%	ASTM D1204-94
Shrink (MD/TD)	200°F, 30 min	1%	ASTM D1204-94
Glass Transition:	°F	-49	
Melting Range:	°F	257 -275	

The information and suggestions contained herein represent the best information available to VCF Films, Inc., and we believe them to be reliable. They should not, however, be construed as controlling and are present without guarantee of performance either express or implied. We urge purchasers to conduct confirmatory tests to determine final suitability for their specific use. No statement with respect to use is intended as a positive recommendation for such use and no warranty with respect to infringement of patents held by others is made or intended.